

VAPOR 150

VAPOUR CONTROL MEMBRANE



COMPOSITION

- 1 top layer: non-woven PP fabric
- 2 middle layer: vapour control PP film
- 3 bottom layer: non-woven PP fabric



AUS AS/NZS 42001 Class 2	USA IRC Class 2	A Önorm B4119 DB	CH SIA 232 V.u. Max 90mm	D ZVDH 0h	F DTU 31.2 B5 d5e E1 Sd2 TR1	I UNI T1470 B/R1	
------------------------------------------	------------------------------	----------------------------------	------------------------------------------	------------------------	----------------------------------------------	-------------------------------	--

TECHNICAL DATA

Properties	standard	value	USC units
Mass per unit area	EN 1849-2	150 g/m ²	0.49 oz/ft ²
Thickness	EN 1849-2	0,5 mm	20 mil
Water vapour transmission (Sd)	EN 1931	13 m	0.269 US Perm
Tensile strength MD/CD	EN 12311-2	> 250/200 N/50 mm	29/23 lbf/in
Elongation MD/CD	EN 12311-2	> 35/40 %	-
Resistance to nail tearing MD/CD	EN 12310-1	> 130/150 N	29/34 lbf
Watertightness	EN 1928	compliant	-
Water vapour resistance:			
- after artificial ageing	EN 1296/EN 1931	compliant	-
- in the presence of alkalis	EN 1847/EN 12311-2	npd	-
Reaction to fire	EN 13501-1	class E	-
Resistance to penetration of air	EN 12114	< 0,02 m ³ /(m ² h50Pa)	< 0.001 cfm/ft ² at 50Pa
Resistance to temperature	-	-20/80 °C	-4/176 °F
UV stability ⁽¹⁾	EN 13859-1/2	336h (3 months)	-
Thermal conductivity (λ)	-	0,3 W/(m·K)	0.17 BTU/h·ft·°F
Specific heat	-	1800 J/(kg·K)	-
Density	-	approx. 300 kg/m ³	approx. 19 lbf/ft ³
Water vapour resistance factor (μ)	-	approx. 26000	approx. 65 MNs/g
VOC	-	not relevant	-
Water column	ISO 811	> 250 cm	> 98 in

⁽¹⁾Laboratory ageing test data cannot reproduce unforeseeable causes of the product's degradation, or consider the stresses to which it will be subjected during its service life. To ensure its integrity, as a precautionary measure, exposure to weathering during construction should be limited to a maximum of 3 weeks.

Waste classification (2014/955/EU): 17 02 03

CODES AND DIMENSIONS

CODE	description	tape	H	L	A	H	L	A	
			[m]	[m]	[m ²]	[ft]	[ft]	[ft ²]	
V150	VAPOR 150	-	1,5	50	75	5	164	807	30
VTT150	VAPOR 150 TT	TT	1,5	50	75	5	164	807	30